


303 Rec'd PCT/PTO 12 OCT 1998

FORM PTO-1390 OFFICE (REV. 10-95)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK		ATTORNEY'S DOCKET NUMBER	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				JA138 U.S. APPLICATION NO. 09/171049	
INTERNATIONAL APPLICATION NO. PCT/US97/06603		INTERNATIONAL FILING DATE 24 April 1997		PRIORITY DATE CLAIMED 24 April 1996	
TITLE OF INVENTION Absorbent Materials Having Improved Structural Stability In Dry And Wet States And Making Methods Therefor					
APPLICANT(S) FOR DO/EO/US REZAI, Ebrahim (NMN); HSUEH, Kesyin; ; ;					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information.					
<p>1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.</p> <p>2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.</p> <p>3. <input type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(I).</p> <p>4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</p> <p>5. <input checked="" type="checkbox"/> A copy of the International Application was filed (35 U.S.C. 371(c)(2))</p> <p style="margin-left: 40px;">a. <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 40px;">b. <input type="checkbox"/> has been transmitted by the International Bureau.</p> <p style="margin-left: 40px;">c. <input checked="" type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US).</p> <p>6. <input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</p> <p>7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))</p> <p style="margin-left: 40px;">a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 40px;">b. <input type="checkbox"/> have been transmitted by the International Bureau.</p> <p style="margin-left: 40px;">c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</p> <p style="margin-left: 40px;">d. <input checked="" type="checkbox"/> have not been made and will not be made.</p> <p>8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</p> <p>10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).</p> <p>Items 11. to 16. below concern document(s) or information included:</p> <p>11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</p> <p>12. <input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</p> <p>13. <input type="checkbox"/> A FIRST preliminary amendment.</p> <p style="margin-left: 40px;"><input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.</p> <p>14. <input type="checkbox"/> A substitute specification.</p> <p>15. <input checked="" type="checkbox"/> A change of power of attorney and/or address letter.</p> <p>16. <input type="checkbox"/> Other items or information:</p>					
<p>*Express Mail* mailing label number <u>EM03270735645</u></p> <p>Date of Deposit <u>12 Oct. 1998</u></p> <p>I hereby certify that this paper/fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to The Assistant Commissioner of Patents, Washington, D.C. 20231</p> <p><u>Donna C. Butts</u> Administrator Mailing Application</p> <p><u>Donna C. Butts</u> Signature</p>					

U.S. APPLICATION NO. (if known, see 37 CFR 1.5)		INTERNATIONAL APPLICATION NO.		ATTORNEY'S DOCKET NUMBER	
		PCT/US97/06603		JA138	
				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$720	
Surcharge of \$130.00 for furnishing the oath or declaration later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$0	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	41-20 =	19	x \$22.00	\$418	
Independent Claims	7-3 =	4	x \$78.00	\$312	
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			\$250.00	\$0	
TOTAL OF ABOVE CALCULATIONS =				\$1450	
Processing fee of \$130.00 for furnishing the English translation later than [] 20 [] 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$0	
TOTAL NATIONAL FEE =				\$1450	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28,3.31). \$40.00 per property +				\$0	
TOTAL FEES ENCLOSED =				\$1450	
				Amount to be refunded	\$
				charged	\$
<p>a. [] A check in the amount of \$ _____ to cover the above fees is enclosed.</p> <p>b. [x] Please charge my Deposit Account No. <u>16-2480</u> in the amount of \$ <u>1450</u> to cover the above fees. A duplicate copy of this sheet is enclosed.</p> <p>c. [x] The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>16-2480</u>. A duplicate copy of this sheet is enclosed.</p> <p>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</p> <p>SEND ALL CORRESPONDENCE TO:</p>					
M.C. Hentz, Patent Attorney Patent Division The Procter & Gamble Company Winton Hill Technical Center 6083 Center Hill Avenue Cincinnati, OH 45224				 Signature <u>Eileen L. Hughett</u> Name <u>34,352</u> Registration Number	

ABSORBENT MATERIALS HAVING IMPROVED STRUCTURAL STABILITY
IN DRY AND WET STATES AND MAKING METHODS THEREFOR

5

FIELD OF THE INVENTION

The present invention relates to absorbent materials that, upon contacting liquids such as water or body fluids, swell and imbibe such liquids. More specifically, the present invention relates to improved structural stability in the dry and wet states of absorbent materials. The absorbent material of the present invention has particular applicability to absorbent articles such as
10 diapers, adult incontinence pads, sanitary napkins, and the like.

BACKGROUND

15 Water-insoluble, water-swellaable, hydrogel-forming absorbent polymers are capable of absorbing large quantities of liquids such as water, body fluids (e.g., urine, blood, menstrual fluid), industrial fluids and household fluids and are further capable of retaining such absorbed liquids under moderate pressures. These absorption characteristics of such polymer materials make
20 them especially useful for incorporation into absorbent articles such as disposable diapers, adult incontinence pads and briefs, and catamenial products such as sanitary napkins, and the like.

The development of highly absorbent members used in such absorbent articles are the subject of substantial commercial interest. A highly desired
25 characteristic for such absorbent articles is thinness. For example, thinner diapers are less bulky to wear, fit better under clothing, and are less noticeable. They are also more compact in the package, making the diapers easier for the consumer to carry and store. Compactness in packaging also results in reduced distribution costs for the manufacturer and distributor,
30 including less shelf space required in the store per diaper unit.

The ability to provide thinner absorbent articles such as a diaper has been contingent on the ability to develop relatively thin absorbent cores or structures that can acquire and store large quantities of discharged body fluids, particularly urine. In this regard, the use of certain absorbent polymers
35 often referred to as "hydrogels" "superabsorbents" or "hydrocolloid" material, has been particularly important. See, for example, U.S. Patent 3,699,103 (Harper et. al), issued June 13, 1972, and U.S. Patent 3,670,731 (Harmon),

issued June 20, 1972, that disclose the use of such absorbent polymers (hereafter "water-insoluble absorbent hydrogel-forming polymers") in absorbent articles.

Moreover, prior absorbent articles have generally comprised relatively low amounts (e.g., less than about 50% by weight) of absorbent gelling particles of the WAHPs. See, for example, U.S. Patent 4,834,735 (Alemany et. al), issued May 30, 1989. It discloses that an absorbent structure or core contains preferably from about 9 to about 50% of WAHP in the fibrous matrix. Unfortunately several problems are encountered when one attempts to provide a thin absorbent core having more than 50% concentration of absorbent gelling particles by weight.

Conventional absorbent articles have the limitation that the absorbent gelling particles are not immobilized and are free to migrate(shift) during the manufacturing process and/or use(wearing). Migrations(shifting) of the absorbent gelling particles during manufacture can lead to absorbent material handling losses during manufacturing operations as well as nonhomogeneous incorporation of the particles being used. A more significant problem, though, occurs when these absorbent gelling particles of WAHPs migrate during or after swelling. This inability to fix the particles at optimum locations leads to an insufficient urine storage capacity in one area and over-capacity in other areas due to the lack of stability.

One important factor is to minimize and/or eliminate the shifting of particles of WAHPs from the first applying location to another position and handling losses during manufacture.

One problem encountered is the shifting and/or leakage of swollen (e.g., with urine) particles of WAHP due to wear-related movement and pressure on the absorbent article. The inability to fix the particles at optimum location is another issue that results in insufficient urine storage capacity in one area and over-capacity in other areas. Subsequently the absorbent article will leak during use. The shifting of wet particles of WAHPs can cause core shifting and more incidence of gel leakage when in use, especially from an absorbent material containing high concentration of WAHPs.

Yet another important factor that has to be considered is the liquid permeability of WAHPs. It has been discovered that the permeability or flow conductivity of the gel layer formed by swelling in the presence of body fluids is extremely important when these absorbent polymers are used in absorbent cores or members at a high concentration in localized or throughout regions

thereof. It should be noted that lack of liquid permeability or flow conductivity of absorbent polymers may directly impact on the ability of resultant gel layers to acquire and distribute body fluids.

Still another concern of WAHPs used in thinner absorbent article is the
5 jelly and mushy feel when touching and handling the absorbent article after usage. When WAHP is dispersed in region or regions at a high concentration, the swollen gel formed by absorbing body fluids is a gel layer, in which the particulate is mobile and the gel layer collapses when subjected to forces such as pushing, squeezing, etc. when handling the absorbent
10 article after usage. This is why absorbent articles having high concentration of WAHP give users or consumers "wet/mushy" feel when touching or handling them from outside.

Therefore, the present invention seeks to resolve the above problems by providing an absorbent material having improved structural stability in dry and
15 wet status.

SUMMARY

Briefly stated, the present invention relates to absorbent materials having improved structural stability in dry and wet states. These absorbent materials
20 comprise (a) absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer; (b) a polycationic polymer; (c) glue microfibers; and (d) a carrier layer; wherein the polycationic polymer is bonded to the absorbent gelling particles; and the glue microfibers act as an adhesive between the absorbent gelling particles and the carrier layer.
25 Because the glue microfibers are tacky, the absorbent gelling particles comprising a WAHP fix to the desired location on the carrier layer and do not shift to the another area in dry state. In wet state, when the absorbent material contacts liquids such as body fluids, the absorbent gelling particles contained in the absorbent material fix to the location first applied due to
30 bonding of the polycationic polymer to the absorbent gelling particles comprising a WAHP, and the absorbent material does not shift.

The bonds between the absorbent gelling particles to the glue microfibers, which in turn, are bonded to the carrier layer, prevent the absorbent gelling particles from shifting during the manufacturing process. The polycationic
35 polymer bonded to the absorbent gelling particles prevents the particles from shifting after they swell with liquid. Consequently, the absorbent material of the invention has improved liquid acquisition speed and low rewetness when

in use. It has been found that when the absorbent material is contacted with liquids, the absorbent material swells, imbibes such liquids into the absorbent gelling particles, and absorbs even under moderate confining pressures.

In a preferred embodiment of the present invention, the carrier layer is
5 selected from the group consisting of a woven material and a nonwoven material.

These absorbent materials may further comprise the cellulose fibers dispersed in the absorbent gelling particles, wherein the cellulose fibers are adhered to the absorbent gelling particles by the glue microfibers.

10 Preferably, the absorbent material of present invention comprises from about 50% to about 90% of the absorbent gelling particle, from about 0.1% to about 10% of the polycationic polymer, from about 1% to about 10% of the thermoplastic polymeric microfiber and from about 5% to about 50% of the carrier layer by weight.

15 The invention further relates to a method of make the absorbent materials, and the absorbent articles comprising the absorbent materials.

These and other features, aspects, and advantages of the present invention will become better understood with regard to the following description, attended claims and accompanying drawing.

20 BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic view of an apparatus for making the absorbent materials of the present invention.

25 DETAILED DESCRIPTION

The following is a list of definitions for certain terms used herein:

30 "Comprising" means other steps and other ingredients which do not affect the result can be added. The term encompasses the terms "consisting of" and "consisting essentially of".

"Dry state" means the state of the absorbent material during manufacture.

35 "Wet state" means the swollen absorbent materials due to absorption of large quantities of liquids such as water, body fluids, industrial fluids and household fluids, when the absorbent materials of the present invention are used in, e.g., a diaper and worn.

"Structural stability" means immobilizing(fixing) the absorbent materials onto the right position in a diaper where first located.

"WAHP" means a water-insoluble absorbent hydrogel-forming polymer.

5 A. Absorbent Material

The absorbent material of the present invention is capable of absorbing large quantities of liquids such as water, body fluids, industrial fluids and household fluids at a rapid rate and is capable of retaining such fluids under moderate pressures. In particular, the absorbent material of the present
10 invention has an improved structural stability in the dry and wet states, while the absorbent material has a high concentration of WAHPs. Preferably, the absorbent material comprises greater than about 50% by weight of a WAHP. The absorbent materials are no shifting in the dry and wet states.

If one does not adhere the absorbent gelling particles at the desired
15 locations in the dry state, the absorbent gelling particles tend to shift during manufacturing process, resulting in, e.g., clumping of absorbent gelling particles and a lack of uniform distribution of the particles.

If one does not adhere the absorbent gelling particles at the desired locations in the wet state, the particles may shift, resulting in insufficient urine
20 storage capacity in one area and over-capacity in other areas. Subsequently the absorbent article will leak during use(wearing). The shifting of wet absorbent gelling particles of WAHP can cause core shifting and more incidence of gel leakage when in use or wearing, especially from an absorbent article using absorbent materials comprising a high concentration
25 of WAHP.

It is the structural stability in the dry and wet status having a high concentration of WAHP at more than 50% by weight which form the basis for the instant invention over past absorbent materials which have not provided such structural stability in the dry and wet states to the extent now achieved.

30 The absorbent material of the present invention comprises: (a) absorbent gelling particles comprising a WAHP; (b) a polycationic polymer; (c) glue microfibers; and (d) a carrier layer; wherein the polycationic polymer is bonded to the absorbent gelling particles; and the glue microfibers act as an adhesive between the absorbent gelling particles and the carrier layer.

35 The present invention in its aspects contemplates the absorbent materials comprising the absorbent gelling particles, the polycationic polymer bonded to the absorbent gelling particles, the glue microfibers dispersed in the

absorbent gelling particles and the carrier layer. In particular, its object is to fix the absorbent gelling particles to the desired location of the carrier layer by an adhesive glue microfiber in the dry state and to fix the absorbent gelling particles bonding to the polycationic polymer on the surface, when the absorbent materials contact liquids such as body fluids in the wet state.

The glue microfiber used herein can be meltblown to form fibers that are tacky in at least one step of the manufacture of the absorbent materials. It is possible that the glue microfiber are initially fixed the absorbent gelling particles to the desired location of the absorbent materials during the manufacturing process.

Generally, one can use any polymer as glue microfibers that are sufficiently tacky, to hold onto the particles that contact it, and thereby qualify as an adhesive polymer. Preferably, the melt blown adhesive polymers which can be utilized for forming the absorbent materials include the elastomeric and non-elastomeric polymers. These polymers must be tacky enough to be blown into fiber forms. The tackiness can be modified with the usage of tackifying resins, which include rosin esters, mixed polyalkenes, polyterpenes, waxes, or incorporating carboxylic acid contained polymers or oligomers within the adhesive resin. Also contemplated by the invention are the use of blends of adhesive polymers, or blends of adhesive polymers and other polymers.

Useful elastomeric polymers include polyolefins and blends (e.g., polypropylene, polybutylene, or ethyleneacrylic acid copolymers), ethylenevinyl acetate copolymers, polyamides, polyesters, and reactive polyamide and polyesters.

Pressure sensitive adhesives are also useful for forming the absorbent structure of this invention. They are permanently tacky and do not change their physical state from an initial liquid to a solid after final bond formation. Exemplified elastomeric polymers are ethylenevinyl acetate copolymer, styrene/diene triblock copolymer, poly(vinylether)s, polyacrylates, and silicones. Thermoplastic elastomeric triblock copolymers of the ABA type have great adhesive capability and processing convenience in this invention. The end block (A) in these polymers are plastic in nature with a high glass transition (or melt) temperature, which the block (B) is rubbery. In particular, the styrene-butadiene-styrene, styrene-isoprene-styrene, styrene-ethylene-co-propylene-styrene copolymers are very useful in this invention.

The non-elastomeric polymer may be a non-elastomeric fiber forming resin or blend containing the same. For example, such polymers include polyolefins, non-elastomeric polyamides, cellulosic derived polymers, vinyl chlorides, and polyvinyl alcohols.

- 5 In a preferred embodiment of the present invention, the types of elastomeric Styrene-Isoprene-Styrene block copolymers are HL-1358 or Finely H-6752A supplied by Fuller Co. The types of non-elastomeric glue microfiber include polyethyloxazoline, for example XR-2676 (Fuller Co.), polyvinylpyrrolidone, for example H-1716 (Fuller Co.) and
- 10 ethylenevinylacetate copolymer, for example HT-480 (Fuller Co.). The glue microfibers comprising polyethyloxazoline would provide the absorbent article comprising the absorbent material of the present invention sufficient structural integrity in the dry state, while in the wet state the polycationic polymers comprising polyethyleneimine are activated to maintain the structural integrity
- 15 of the absorbent article.

- The polycationic polymer used herein is a polymer which has multiple functional groups that are capable of bonding to the surface of the absorbent gelling particles. In a preferred embodiment, an amino-group or iminegroup containing polymer is used as the polycationic polymer. Such polycationic
- 20 polymers include polyamines, polyimines and mixtures thereof. More preferably, the polyamine is selected from the group consisting of polymers having first amine groups (e.g., polyvinylamine, polyallylamine), polymers having second amine groups (e.g., polyethyleneamines) and polymers having third amine groups (e.g., poly-N, N- dimethylalkyl amine, poly-N-alkylamine).
- 25 The polyimines preferably used include polyethyleneimines, modified polyethyleneimines crosslinked with epihalohydrine, polyamidoamines grafted with ethyleneimine and mixtures thereof. Other suitable polycationic polymers include modified polyamidoamine grafted with ethyleneimine, polyetheramine, polyvinylamine, polyallylamine, polyamidopolyamine and
- 30 mixtures thereof.

- In a preferred embodiment, the polycationic polymer is a cationic polymer having an average molecular weight of at least about 200, more preferably of at least more than 5,000, and most preferably of more than about 10,000. The polycationic polymers useful in the invention include those polymers
- 35 having a single maximum value (a peak) in molecular weight distribution, as well as those polycationic polymers having one or more maximum values.

The molecular weight distribution can be analyzed by, for example, gel permeation chromatography.

Preferably, the amount of polycationic polymer used in the absorbent material is from about 0.1% to 10% by weight of the absorbent materials.

- 5 For providing a high concentration of a WAHP, such as more than 50% by weight of the absorbent material, the polycationic polymer used for the present invention has a concentration of from about 80% to 99% by weight so that it can be tacky by itself. The polycationic polymers having the characteristic of tackiness can be meltblown without glue microfibers, consequently acting as an adhesive between the absorbent gelling particles and the carrier layer. Preferably, the polycationic polymer fiber has a molecular weight of at least about 70,000.

B. Water-insoluble Absorbent Hydrogel-forming Polymer

15 1. Chemical Composition

- The WAHPs useful in the present invention are commonly referred to as "hydrogel-forming", "hydrocolloid", or "superabsorbent" polymers and can include polysaccharides such as carboxymethyl starch, carboxymethyl cellulose, and hydroxypropyl cellulose; nonionic types such as polyvinyl alcohol, and polyvinyl ethers; cationic types such as polyvinyl pyridine, polyvinyl morpholinone, and N,N-dimethylaminoethyl or N,N-diethylaminopropyl acrylates and methacrylates, and the respective quaternary salts thereof. Typically, WAHPs useful in the present invention have a plurality of anionic, functional groups, such as sulfonic acid, and more typically carboxy, groups. Examples of polymers suitable for use herein include those which are prepared from polymerizable, unsaturated, acid-containing monomers. Thus, such monomers include the olefinically unsaturated acids and anhydrides that contain at least one carbon to carbon olefinic double bond. More specifically, these monomers can be selected from olefinically unsaturated carboxylic acids and acid anhydrides, olefinically unsaturated sulfonic acids, and mixtures thereof.

- Some non-acid monomers can also be included, preferably in minor amounts, in preparing the WAHPs herein. Such non-acid monomers can include, for example, the water-soluble or water-dispersible esters of the acid-containing monomers, as well as monomers that contain no carboxylic or sulfonic acid groups at all. Optional non-acid monomers can thus include monomers containing the following types of functional groups: carboxylic

acid or sulfonic acid esters, hydroxyl groups, amide-groups, amino groups, nitrile groups, quaternary ammonium salt groups, aryl groups (e.g., phenyl groups, such as those derived from styrene monomer). These non-acid monomers are well-known materials and are described in greater detail, for example, in U.S. Patent 4,076,663 (Masuda et. al), issued February 28, 1978, and in U.S. Patent 4,062,817 (Westerman), issued December 13, 1977.

Olefinically unsaturated carboxylic acid and carboxylic acid anhydride monomers include the acrylic acids typified by acrylic acid itself, methacrylic acid, ethacrylic acid, -chloroacrylic acid, -cyanoacrylic acid, -methyacrylic acid (crotonic acid), -phenylacrylic acid, -acryloxypropionic acid, sorbic acid, -chlorosorbic acid, angelic acid, cinnamic acid, p-chlorocinnamic acid, -sterylacrylic acid, itaconic acid, citroconic acid, mesaconic acid, glutaconic acid, aconitic acid, maleic acid, fumaric acid, tricarboxyethylene and maleic acid anhydride.

Olefinically unsaturated sulfonic acid monomers include aliphatic or aromatic vinyl sulfonic acids such as vinylsulfonic acid, allyl sulfonic acid, vinyl toluene sulfonic acid and styrene sulfonic acid; acrylic and methacrylic sulfonic acid such as sulfoethyl acrylate, sulfoethyl methacrylate, sulfopropyl acrylate, sulfopropyl methacrylate, 2-hydroxy-3-methacryloxypropyl sulfonic acid and 2-acrylamide-2-methylpropane sulfonic acid.

Preferred WAHPs for use in the present invention contain carboxy groups. These polymers include hydrolyzed starch-acrylonitrile graft copolymers, partially neutralized hydrolyzed starch-acrylonitrile graft copolymers, starch-acrylic acid graft copolymers, partially neutralized starch-acrylic acid graft copolymers, saponified vinyl acetate-acrylic ester copolymers, hydrolyzed acrylonitrile or acrylamide copolymers, slightly network crosslinked polymers of any of the foregoing copolymers, partially neutralized polyacrylic acid, and slightly network crosslinked polymers of partially neutralized polyacrylic acid. These polymers can be used either solely or in the form of a mixture of two or more different polymers. Examples of these polymer materials are disclosed in U.S. Patent 4,076,663 (Masuda et. al), issued February 28, 1978, U.S. Patent 4,093,776 (Aoki et. al), issued June 6, 1978, U.S. Patent 4,666,983 (Tsubakimoto et. al), issued May 19, 1987, and U.S. Patent 4,734,478 (Tsubakimoto et. al), issued March 29, 1988.

More preferably polymer materials used in making the WAHPs are slightly network crosslinked polymers of partially neutralized polyacrylic acids and

starch derivatives thereof. More preferably still, the WAHPs comprise from about 50 to about 95%, more preferably about 75%, neutralized, slightly network crosslinked, polyacrylic acid (i.e., poly (sodium acrylate/acrylic acid)). Network crosslinking renders the polymer substantially water-insoluble and, in part, determines the absorptive capacity and extractable polymer content characteristics of the WAHPs. Processes for network crosslinking these polymers and typical network crosslinking agents are described in greater detail in U.S. Patent 4,076,663 (Masuda et. al), issued February 28.

Surface crosslinked WAHPs are used in a preferred embodiment of the present invention. They have a higher level of crosslinking in the vicinity of the surface than in the interior. As used herein, "surface" describes the outer-facing boundaries of, e.g., the particle, fiber. For porous WAHPs (e.g., porous particles), exposed internal boundaries can also be included. By a higher level of crosslinking at the surface, it is meant that the level of functional crosslinks for the WAHP in the vicinity of the surface is generally higher than the level of functional crosslinks for the WAHP in the interior.

The gradation in crosslinking from surface to interior can vary, both in depth and profile. Thus, for example, the depth of surface crosslinking can be shallow, with a relatively sharp transition to a lower level of crosslinking. Alternatively, for example, the depth of surface crosslinking can be a significant fraction of the dimensions of the WAHP, with a broader transition.

Depending on size, shape, porosity as well as functional considerations, the degree and gradient of surface crosslinking can vary within a given WAHP. For particulate WAHPs, surface crosslinking can vary with particle size, porosity, etc. Depending on variations in surface/volume ratio within the WAHP (e.g., between small and large particles), it is not unusual for the overall level of crosslinking to vary within the material (e.g., be greater for smaller particles).

Surface crosslinking is generally accomplished after the final boundaries of the WAHP is essentially established (e.g., by grinding, extruding, foaming, etc.) However, it is also possible to effect surface crosslinking concurrent with the creation of final boundaries. Furthermore, some additional changes in boundaries can occur even after surface crosslinks are introduced.

The surface crosslinking can be accomplished before or, simultaneously, with the covalent bonding of the polycationic polymer to the surface of the absorbent gelling particles.

While the WAHP is preferably of one type (i.e., homogeneous), mixtures of polymers can also be used in the present invention. For example, mixtures of starch-acrylic acid graft copolymers and slightly network crosslinked polymers of partially neutralized polyacrylic acid can be used in the present invention.

2. Physical Forms

The absorbent gelling particles used in the present invention can have a size, shape and/or morphology varying over a wide range. The absorbent gelling particles may have a large ratio of greatest dimension to smallest dimension (e.g., granules, flakes, pulverulents, interparticle aggregates, interparticle crosslinked aggregates, and the like) and can be in the form of fibers, foams, and the like.

For particles of WAHPs useful in the present invention, the particle size is in the range of from about 10 to about 1000 microns. The WAHPs can also comprise mixtures with low levels of one or more additives, such as, for example, powdered silica, surfactants, cellulose microfiber and the like. The components in this mixture can be physically and/or chemically associated in a form such that the WAHP component and the non-hydrogel-forming polymer additive are not readily physically separable. The WAHPs can be essentially non-porous or have substantial internal porosity.

For particles as described above, particle size is defined as the dimension determined by sieve size analysis. Thus, for example, a particle that is retained on a U.S.A. Standard Testing Sieve with 710 micron openings (e.g., No. 25 U.S. Series Alternate Sieve Designation) is considered to have a size greater than 710 microns; a particle that passes through a sieve with 710 micron openings and is retained on a sieve with 500 micron openings (e.g., No. 35 U.S. Series Alternate Sieve Designation) is considered to have a particle size between 500 and 710 microns; and a particle that passes through a sieve with 500 micron openings is considered to have a size less than 500 microns.

C. Absorbent Article comprising the Absorbent Materials

The absorbent materials according to the present invention can be used for many purposes in many fields of use. For example, the absorbent material can be used for packing containers; drug delivery devices; wound cleaning devices; burn treatment devices; ion exchange column materials;

construction materials; agricultural or horticultural materials such as seed sheets or water-retentive materials; and industrial uses such as sludge or oil dewatering agents, materials for the prevention of dew formation, desiccants, and humidity control materials. In these environments, the absorbent material of the invention can have a number of shapes and sizes. For example, the absorbent material can be in the form of sheets, films, cylinders, blocks or other shaped elements. The absorbent material can comprise a cellulosic material for enhancing absorbency and/or be in a form amenable to these and other applications as described hereinafter.

Because of the unique absorbent properties of the absorbent material of the present invention, it is especially suitable for use as an absorbent core in absorbent articles, especially disposable absorbent articles. As used herein, the term "absorbent article" refers to articles which absorb and contain body fluids and more specifically refers to articles which are placed against or in proximity to the body of the wearer to absorb and contain the various fluids discharged from the body. Additionally, "disposable" absorbent articles are those which are intended to be discarded after a single use (i.e., the original absorbent article in its whole is not intended to be laundered or otherwise restored or reused as an absorbent article, although certain materials or all of the absorbent article may be recycled, reused, or composted).

In general, an absorbent article comprise (a) a liquid pervious topsheet; (b) a liquid impervious backsheet; and (c) an absorbent core positioned between the topsheet and the backsheet wherein the absorbent core comprises at least one absorbent material. As used herein, the term "absorbent core" refers to the component of the absorbent article that is primarily responsible for fluid handling properties of the article, including acquiring, transporting, distributing and storing body fluids. As such, the absorbent core preferably does not include the topsheet or backsheet of the absorbent article.

In a more preferred embodiment, the absorbent core or absorbent member can further comprise fibers or fluff pulp (fibrous or fiber material); more specifically, non-absorbent-gelling fibers. Such fiber material can be used as a reinforcing or absorbent member in the absorbent core, improving fluid handling of the core, as well as serving as a co-absorbent with the absorbent polymers. As used herein, the term "absorbent member" refers to the components of the absorbent core that typically provide one or more fluid handling properties, e.g., fluid acquisition, fluid distribution, fluid

transportation, fluid storage, etc. The absorbent member can comprise the entire absorbent core or only a portion of the absorbent core, i.e., the absorbent core can comprise one or more absorbent members.

Any type of fiber material which is suitable for use in conventional absorbent products can be used in the absorbent core or absorbent member herein. Specific examples of such fiber material include cellulose fibers, improved cellulose fibers, rayon, polypropylene, and polyester fibers such as polyethylene terephthalate (DACRON), hydrophilic nylon (HYDROFIL), and the like. Examples of other fiber materials for use in the present invention in addition to some already discussed are hydrophilized hydrophobic fibers, such as surfactant-treated or silica-treated thermoplastic fibers derived, for example, from polyolefins such as polyethylene or polypropylene, polyacrylics, polyamides, polystyrenes, polyurethanes and the like. In fact, hydrophilized hydrophobic fibers which are in and of themselves not very absorbent and which, therefore, do not provide webs of sufficient absorbent capacity to be useful in conventional absorbent structures, are suitable for use in the absorbent core by virtue of their good wicking properties. This is because, in the absorbent core herein, the wicking propensity of the fibers is as important, if not more important, than the absorbent capacity of the fiber material itself due to the high rate of fluid uptake and lack of gel blocking properties of the absorbent core. Synthetic fibers are generally preferred for use herein as the fiber component of the absorbent core. More preferred are polyolefin fibers, preferably polyethylene fibers.

Other cellulosic fiber materials which can be useful in certain absorbent cores or absorbent members herein are chemically stiffened cellulosic fibers. Preferred chemically stiffened cellulosic fibers are the stiffened, twisted, curled cellulosic fibers which can be produced by internally crosslinking cellulose fibers with a crosslinking agent. Suitable stiffened, twisted, curled cellulose fibers useful as the hydrophilic fiber materials herein are described in greater detail in U.S. Patent 4,888,093 (Dean et. al), issued December 19, 1989; U.S. Patent 4,889,596 (Herron et. al), issued December 26, 1989; U.S. Patent 4,889,596 (Schoggen et. al), issued December 26, 1989; U.S. Patent 4,889,597 (Bourbon et. al), issued December 26, 1989; and U.S. Patent 4,898,647 (Moore et. al), issued February 6, 1990.

A preferred embodiment of the disposable absorbent article is a diaper. As used herein, the term "diaper" refers to a garment, generally worn by infants and incontinent persons, that is worn about the lower torso of the

wearer. A preferred diaper configuration for a diaper comprising an absorbent core is described generally in U.S. Patent 3,860,003 (Buell), issued January 14, 1975. Alternatively preferred configurations for disposable diapers herein are also disclosed in U.S. Patent 4,808,178 (Aziz et. al), issued February 28, 1989; U.S. Patent 4,695,278 (Lawson), issued September 22, 1987; U.S. Patent 4,816,025 (Foreman), issued March 28, 1989; and U.S. Patent 5,151,092 (Buell et. al.), issued September 29, 1992.

Another preferred embodiment of the disposable absorbent article is a catamenial product. Preferred catamenial products comprise a formed-film, apertured topsheet as disclosed in U.S. Patent 4,285,343 (McNair), issued August 25, 1981; U.S. Patent 4,608,047 (Mattingly), issued August 26, 1986; and U.S. Patent 4,687,478 (Van Tilburg), issued August 18, 1987.

Preferred catamenial products can comprise wings, side flaps, and other structures and elements, as described in co-pending, commonly assigned U.S. application serial No. 984,071, to Yasuko Morita, entitled "Absorbent Article Having Elasticized Side Flaps", filed November 30, 1992.

It should be understood, however, that the present invention is also applicable to other absorbent articles known commercially by other names, such as incontinent briefs, adult incontinent products, training pants, diaper inserts, facial tissues, paper towels, and the like.

D. Process for Making Absorbent Material

FIG. 1 illustrates a preferred apparatus useful in the process of the present invention. The forming apparatus generally indicated as 1, is composed of a particle applying unit 10, and a carrier layer apparatus 11. The particle applying unit 10 includes an absorbent gelling particles applying unit 12, a glue microfibers applying unit 16 and a polycationic polymer spray unit 17. The absorbent gelling particles are first loaded in, for example, a K-tron screw feeder 12 for continuously feeding absorbent gelling particles to Vibratory feeder 13 and then hopper 14. After absorbent gelling particles are carried away from the outlet of hopper 14 into an eductor 15, absorbent gelling particles leave the nozzle 16 as the first air stream 21 by about 50-psi air stream. The eductor 15 and the nozzle 16 concentrates the absorbent gelling particles into a constant flow in order to inject the absorbent gelling particles through the glue microfibers. Preferably the average diameter of the absorbent gelling particle is usually from about 10 microns to about 1,000 microns. While the absorbent gelling particles are predominately

discontinuous, they generally have a length exceeding that normally associated with particles.

The glue microfibers are extruded via glue gun 17 (J&M Co.) with rate between about 0.2 to about 2.0 Kgcm⁻¹hr⁻¹ as the second air stream 22.

5 The glue microfibers extrusion thins out when guided through a second air stream. The temperature range is set up enough to solute and spray the glue microfibers. The air gap is preferably kept about 0.18 mm. The second air stream of glue microfibers is controlled to preferably deliver about 10 g/m² basis weight of the resulting absorbent material and the operation range is
10 preferably from about 3.0 gm/m² to about 50.0 gm/m².

The first air stream 21 is merged with the second air stream 22 to form an integrated air stream 23. The integrated air stream 23 is injected onto a carrier layer in mechanical direction, preferably about 70 meter/min. The injection rate of integrated air stream 23 preferably is about 1.0 m/sec which
15 is adjusted to match the carrier unit's speed.

A vacuum conveyor 19 is placed beneath the nozzle 16 and the glue gun 17. As the carrier layer 25 is run through the vacuum conveyor 19, the incoming integrated air stream 23 is attracted and firmly attached to the carrier layer 25. The absorbent gelling particles cover the center line of the
20 carrier layer, preferably at least one half of the width.

A third air stream containing pre-agitated polycationic polymer is located after laydown of the absorbent gelling particles applying unit 18. The third air stream is sprayed onto the absorbent gelling particles attached to the carrier layer and the polycationic polymer bonds to the absorbent gelling particles on
25 the surface. The line speed is controlled preferably at about 8 gm/m².

A folding board 20 is placed adjacent to the polycationic polymer unit 18. The absorbent material comprising the absorbent gelling particles, the glue microfibers, the polycationic polymer and the carrier layer are folded to form an edge closed laminate structure of final width. The laminated product of
30 absorbent material is wound at the end of the line.

The present invention also provides a method for making the absorbent material. The method comprises (a) applying absorbent gelling particles comprising a WAHP onto a carrier layer; (b) applying glue microfibers onto the carrier layer; and (c) applying a polycationic polymer onto the absorbent
35 gelling particles to form a bond between the absorbent gelling particles and the polycationic polymer; wherein the absorbent gelling particles adhere to the glue microfibers prior to the glue microfibers adhering to the carrier layer.

In one embodiment, the method further comprises the step of dispersing cellulose fibers into the absorbent gelling particles, wherein the glue microfibers act as an adhesive between the cellulose fibers and the absorbent gelling particles.

- 5 In a preferred embodiment, the absorbent gelling particles are applied via a first air stream on a carrier layer.

In more preferred embodiment, the glue microfibers are applied via the second air stream. The second air stream comprising glue microfibers preferably has a temperature of from about 100°C to about 400°C.

- 10 In a preferred embodiment, the polycationic polymer is applied via the third air stream. The third air stream comprising the polycationic polymer is used as a solution having a concentration preferably from about 0.1% to about 10% by weight.

- The solution containing the polycationic polymer is then applied to a plurality of the absorbent gelling particles. In particular, at least two, preferably all, of the absorbent gelling particles have at least some portion covered with the solution. In a preferred embodiment, at least 70% of the surface area of the gelling particles are covered with the solution applied thereon. The solution can be applied using any of the various techniques and apparatus well known in the art which are suitable for applying a solution to a material including coating, dumping, pouring, dropping, spraying, atomizing, condensing, or immersing the solution onto the absorbent gelling particles. After the polycationic polymer is applied, preferably greater than about 90% of the surface area of the gelling particles is covered with the solution.
- 15
20
25

In a preferred embodiment, the method further comprises the step of heating the resulting material of step (c) at a temperature of from about 50°C to about 300°C so as to covalently bond the polycationic polymer to the WAHP of the absorbent gelling particles.

- 30 In a preferred embodiment, the polycationic polymer are reacted with the absorbent gelling particles such that the polycationic polymer becomes covalently bonded to the absorbent gelling particles at the surface area of the absorbent gelling particles. More preferably, the covalent bonds are made between the surface-located carboxy groups of the absorbent gelling particles and the amino groups of the polycationic polymer. Preferably, at least about 80% more preferably more than about 90% by weight of the polycationic polymer is covalently bonded to the absorbent gelling particles. When
- 35

supplied with higher thermal energy, the absorbent articles comprising the absorbent material have more fluid permeable. With the improved fluid permeability the spreading of, e.g., urine throughout the absorbent articles comprising the absorbent material is increased, and therefore the absorbent gelling particles fluid absorption efficiency can be raised.

The present invention also relates to a method of making an absorbent material. The method comprises (a) forming a first air stream comprising absorbent gelling particles comprising a WAHP; (b) forming a second air stream comprising glue microfibers; (c) merging the second air stream with the first air stream to form an integrated air stream comprising a through mixture of the glue microfibers and the absorbent gelling particles; (d) directing the integrated air stream onto a carrier layer; (e) forming a third air stream comprising a polycationic polymer; and (f) directing the third air stream onto the carrier layer so the polycationic polymer bonds to the absorbent gelling particles.

Preferably, the method of forming an absorbent material comprises (a) forming a first air stream comprising absorbent gelling particles comprising a WAHP; (b) forming a second air stream comprising a polycationic polymer; (c) merging the second air stream with the first air stream to form an integrated air stream, wherein the polycationic polymer bonds to the absorbent gelling particles; (d) forming a third air stream comprising glue microfibers; (e) merging the integrated air stream with the third air stream to form a mixture air stream; and (f) directing the mixture air stream onto a carrier layer so the absorbent gelling particles bonded to the polycationic polymer adhere to the glue microfibers, and the glue microfibers adhere to the carrier layer.

In a more preferred embodiment, the second air stream is formed a temperature of at least about 400°C and about 50 psi air pressure at sonic velocity.

In another embodiment, the method comprises (a) applying polycationic polymer fibers comprising a polycationic polymer having a concentration of from about 80% to about 99% by weight onto absorbent gelling particles comprising a WAHP; and (b) applying the absorbent gelling particles onto a carrier layer; wherein the polycationic polymer fibers act as an adhesive between the absorbent gelling particles and the carrier layer. Preferably, the polycationic polymer fiber has the molecular weight of at least about 70,000.

In a preferred embodiment, the polycationic polymer fibers form a first air stream containing the polycationic polymer fibers and the absorbent gelling particles from the second air stream to form an integrated air stream containing a thorough mixture of the polycationic polymer fibers and the absorbent gelling particles.

In a more preferred embodiment, the method comprises (a) forming a first air stream containing polycationic polymer fibers; (b) forming a second air stream containing absorbent gelling particles comprising a WAHP; (c) merging the second air stream with the first air stream to form an integrated air stream, wherein the polycationic polymer fibers bond to the absorbent gelling particles; and (d) directing the integrated air stream onto a carrier layer so that the absorbent gelling particles bond to the polycationic polymer fibers on the carrier layer.

E. Test Methods

1. Synthetic Urine

The specific synthetic urine used in the test methods set forth herein is referred to as "Synthetic Urine". The Synthetic Urine is commonly known as Jayco SynUrine or Jayco Synthetic Urine and is available from Jayco Pharmaceuticals Company of Camp Hill, Pennsylvania. The formula for the Synthetic Urine is: 2.0 g/l of KCl; 2.0 g/l of Na₂SO₄; 0.85 g/l of (NH₄)H₂PO₄; 0.15 g/l (NH₄)H₂PO₄; 0.19 g/l of CaCl₂ and 0.23 g/l of MgCl₂. All of the chemicals are of reagent grade. The PH of the Synthetic Urine is in the range of 6.0 to 6.4.

25

2. Wet Burst Strength Measurement

The standard burst test program measures load, deflection and energy at peak load, and fail load at test end. The purpose of this test is to evaluate the gram force of a absorbent-gelling-particle-contained laminate structure after subjecting to a constant loading of synthetic urine. Laminate samples with a dimension of 10 cm x 10 cm and of 310 gm/m² absorbent gelling particle basis weights, typically weigh at 3.6 ± 0.3 gm and are allowed to soak in 70mL of synthetic urine. Synthetic urine is fully absorbed by the absorbent-gelling-particle-contained laminate, with 20 times synthetic urine loading of its original weight. A burst tester, Thwing-Albert Instrument Co. No. 177-1-B, is used to measure the gram force needed to puncture the 20 time's synthetic urine-loaded laminate samples. The sample holder is a plexi

glass disk of 4.5-inch diameter and 0.125 inch of thickness, and with a hole of 0.75 inch diameter in the center of plexiglass. A stainless ball head of 0.25-inch diameter is used to puncture the samples.

5 3. Tea Bag Gel Volume

10 Gel volume of a WAHP is defined as its retention absorbent capacity after swollen in an excess of Jaycee Synthetic Urine. It provides a measure of the maximum absorbent capacity of the polymer under conditions of use where the pressures on the polymer are relatively low. Gel volume is determined by
15 centrifuge capacity method described below by using the Jaycee Synthetic Urine. The gel volume is calculated on a dry-weight basis. The dry weight used in the gel volume calculation is determined by oven drying the WAHP at 105°C for three hours. All of the chemicals are of reagent grade. The pH of the Jaycee Synthetic Urine is in the range of 6.0 to 6.4.

20 Heat-sealable tea-bag paper is cut into 6cm x 12cm, folded in half lengthwise and sealed close to the edge along two sides with a T-bar sealer to produce 6cm x 6cm tea bag squares. 0.200(± 0.005) gm of a WAHP is transferred into a tea-bag, and the top of the bag is sealed at its edge. The top of an empty tea-bag is sealed and is used as a blank. Approximately
25 300ml of Jayco Synthetic Urine is poured into a 1,000ml beaker, and the tea-bag containing WAHP and the blank are submerged into the beaker. After being soaked for 30 minutes, the blank and the WAHP-filled tea bag are removed from the solution by using tongs. A centrifuge (H-122 type, Kokusan Enshinki Co. Ltd., Tokyo, Japan) with a direct read tachometer,
30 electric timer is used for this measurement. The sample tea bags and the blank tea bags are positioned in the centrifuge basket and centrifuged at 1100rpm for three minutes. Gel volume is calculated as follows:

$$\text{Gel volume (g/g)} = (W_s - W_b - W_o) / W_o$$

35 wherein W_s is the sample tea bag weight after centrifuge, W_b is the blank tea bag weight after centrifuge, W_o is the WAHP weight (0.200g).

The average of at least two determinations should be reported.

40 4. Acquisition Speed and Re-wet Test

The Acquisition Speed and Rewetness, which are the laminate production properties comprising this absorbent material made according to present

invention, are evaluated in diapers. The typical diaper design includes airfilt as the acquisition layer and the laminate production as fluid storage core of at least 310 gm/m² absorbent gelling particle basis weight. The acquisition speed and rewet measurements are performed with 0.30 psi external pressure in a flat configuration. After continuous loading of 200 mL synthetic urine, several pieces of filter papers are placed on the wet pad and allowed to soak for 30 min under 0.40 psi. The rewet values, as measured from the weight increase of filter paper, are summed up from front, middle, to back part of diaper.

10

F. Examples

The following examples are presented for purposes of illustrating various aspects of the absorbent material of the invention and are not intended as limiting the scope of the appended claims in any way.

15 A composite in accordance with the present invention is prepared on a process line for laminate production illustrated in FIG 1.

All raw materials used in this example are obtained from commercial sources. Styrene-Isoprene-Styrene block copolymer (HL-1358-XZP) produced by H.B. Fuller Co. is used as a glue microfiber, and is heated and kept at least 350°C during laminate production process. L76lf produced by Nippon Shokubai Co. Ltd. is used as absorbent gelling particles, and has particle size distribution ranging from 300µm to 600µm. The Polyethyleneimine produced by Wako Chem Co., is used as a polycationic polymer, and is a 30% solid and has molecular weight of 70,000 Daltons. A tissue produced by Havix Company LTD is used as a wet laid tissue of 18 gms and has the tensile strength of 1.1 Kg/in in mechanical direction.

The properties of the absorbent material, Wet Burst Strength (BBS) and absorbent capacity (GV) are evaluated and presented in Table 1. In a diaper including the absorbent material of present invention. Acquisition speed and Rewet performances are evaluated and presented in Table 2.

EXAMPLE 1

L76lf is prepared in K-tron screw feeder. L76lf is loaded in a K-tron screw feeder for continuously feeding L76lf into a vibrator feeder and then a hopper. A compressed air stream is kept at 50 psi air pressure. L76lf is carried away from the outlet of the hopper into an educator and is combined with the compressed air stream, so as to provide a first air stream. Injection rate of

35

the first air stream of L76lf is kept about 1.0 msec^{-1} which is adjusted to match the web line speed.

Styrene-Isoprene-Styrene block copolymer (HL-1358-XZP), is prepared in the apparatus of glue gun (J&M Co.). HL-1358-XZP is extruded through glue gun at a rate between about 0.2 to about $2.0 \text{ Kgcm}^{-1}\text{hr}^{-1}$. The air gap of the glue gun is kept at about 0.18 mm , as the glue block-copolymer becomes thin fibers.

The extruded HL-1358-XZP is combined with an air stream, so as to provide a second air stream. The second air stream is kept at a temperature of about 400°C and about 50 psi air pressure at about sonic velocity. The second air stream of HL-1358-XZP is controlled to deliver 10 g/m^2 basis weight of the laminate production. The operation range of the second air stream can be between about 3.0 gm/m^2 and about 50.0 gm/m^2 .

The first air stream of L76lf is subsequently injected through the second air stream of HL-1358-XZP, to form an integrated air stream, onto a vacuum conveyor.

The vacuum conveyor is placed beneath the glue gun and the educator.

At the same time, a tissue is introduced to the vacuum conveyor at a typical speed of about 70 meter/min. As the tissue is run over the vacuum conveyor, the incoming integrated air stream is attracted and firmly attached to the tissue. The tissue width is at least about 23 cm and a coverage width of the integrated air stream is at least about 9.50 cm .

A polyethyleneimine is dissolved in distilled water at a concentration of from about 10 to about 20% by weight. A third air stream spray is forwarded an air pressure spray system (B1/8 BAU-SS+SUV 67-SS from Spraying System Co. of $0.5\text{-}1.2 \text{ Kg/cm}^2$) containing a pre-agitated solution of polyethyleneimine and water is located after the integrated air stream containing HL-1358-XZP and L76lf laydown. According to the line speed, the speed-of spraying and the level of polyethyleneimine solution is controlled at 8 gm/m^2 , which is equal to about 2.0% by weight of the laminate production.

A folding board is placed next to the third air stream spray of polyethyleneimine solution. Tissue, L76lf, HL-1358-XZP and polyethyleneimine are folded to form an edge closed laminate structure of about 10 cm final width. The laminate production is wound at the end of the line. The thickness of a formed laminate of about 310 gm/m^2 absorbent gelling particle is about 1.3 mm .

The laminate production properties comprising this absorbent material made according to this example are evaluated. The Wet Burst Strength and The Tea Bag gel Volume is 61 gm and 33 g/g. The results surprisingly illustrate the higher gel strength (BBS) and high absorbent capacity (GV) achieved by the absorbent material according to the present invention.

EXAMPLE 2

The basic composition of sample is similar to Example 1, except no third air stream spray of polyethyleneimine additive is used.

The laminate production properties comprising this absorbent material made according to this example are evaluated. The Wet Burst Strength and The Tea Bag gel Volume is 25 gm and 35 g/g.

EXAMPLE 3

In this example, the basic composition of sample is similar to Example 1, except as set forth below.

(1) "URIC absorbent gelling particle" is prepared in K-tron screw feeder for use in the first air stream. "URIC absorbent gelling particle" is an absorbent gelling particle having improved absorbent property by the absorbent property modification polymer, such as the polycationic polymer, bonded to the absorbent gelling particles.

(2) There is no third air stream spray.

The laminate production properties comprising this absorbent material made according to this example are evaluated. The Wet Burst Strength and The Tea Bag gel Volume is 45 gm and 31 g/g. The results surprisingly illustrate the higher gel strength (BBS) and high absorbent capacity (GV) achieved by the absorbent material according to the present invention.

EXAMPLE 4.

The basic composition of the sample is similar to Example 1, except no second air stream of the thermoplastic polymeric microfiber and the third air stream spray of polyethyleneimine additive are used.

The laminate production properties comprising this absorbent material made according to this example are evaluated. The Wet Burst Strength and The Tea Bag gel Volume is 0gm and 38g/g.

Table-1. Tea bag gel volume and effects on wet strength by adding polyethyleneimine

Samples		Polyethylene imine (%)	Wet Burst Strength (gm)	Tea bag gel volume (g/g)
Sample #1	Polycationic polymer is added <i>in situ</i> during laminate making process.	2	61	33
Sample #2	No polycationic polymer is included.	0	25	35
Sample #3	Polycationic polymer is added during absorbent gelling particle making process. Subsequently this absorbent gelling particle is used to make laminate structure.	2	45	31
Sample #4	No glue microfiber.	0	0	38

5 The acquisition speeds and rewet values are evaluated in a diaper. The diaper is made of by laminate production comprising the absorbent material according to above examples. The properties of the diaper are evaluated and presented in Table 2.

10 Table-2. Acquisition and rewet performances of the invention in diaper application.

Samples	Acquisition Speed (sec)				Pad Rewet (gm) at 200 mL loading of synthetic urine
	50 mL	100mL	150mL	200mL of synthetic urine loading	
Sample #1	20	31	35	43	0.50
Sample #2	18	28	39	55	0.50
Sample #3	16	20	23	28	0.50

15 Diapers of this invention (the sample #1 and #3) show faster acquisition speeds at high urine loading, e.g., urine volume levels of at least 150mL than the Sample #2. The improved acquisition speeds are caused by faster fluid transportation among the well-bonded absorbent gelling particle particulate in the wet state. In Sample #3, where absorbent gelling particle is treated with polyethyleneimine alternatively during absorbent gelling particle production

20 process, the laminate shows even faster acquisition speeds. The degree of bonding forces in Sample #3 is higher than that of Sample #1. Also shown in Table-2, the rewet values of the invention maintain control diaper that is used to the absorbent material of no polycationic polymer.

25 All publications, patent applications, and issued patents mentioned hereinabove are hereby incorporated in their entirety by reference.

It is understood that the examples and embodiments described herein are for illustrative purposes only and that various modifications or changes in light thereof will be suggested to one skilled in the art and are to be included in the spirit and purview of this application and scope of the appended claims.

100 101 102 103 104 105 106 107 108 109 110 111 112 113 114 115 116 117 118 119 120 121 122 123 124 125 126 127 128 129 130 131 132 133 134 135 136 137 138 139 140 141 142 143 144 145 146 147 148 149 150 151 152 153 154 155 156 157 158 159 160 161 162 163 164 165 166 167 168 169 170 171 172 173 174 175 176 177 178 179 180 181 182 183 184 185 186 187 188 189 190 191 192 193 194 195 196 197 198 199 200 201 202 203 204 205 206 207 208 209 210 211 212 213 214 215 216 217 218 219 220 221 222 223 224 225 226 227 228 229 230 231 232 233 234 235 236 237 238 239 240 241 242 243 244 245 246 247 248 249 250 251 252 253 254 255 256 257 258 259 260 261 262 263 264 265 266 267 268 269 270 271 272 273 274 275 276 277 278 279 280 281 282 283 284 285 286 287 288 289 290 291 292 293 294 295 296 297 298 299 300 301 302 303 304 305 306 307 308 309 310 311 312 313 314 315 316 317 318 319 320 321 322 323 324 325 326 327 328 329 330 331 332 333 334 335 336 337 338 339 340 341 342 343 344 345 346 347 348 349 350 351 352 353 354 355 356 357 358 359 360 361 362 363 364 365 366 367 368 369 370 371 372 373 374 375 376 377 378 379 380 381 382 383 384 385 386 387 388 389 390 391 392 393 394 395 396 397 398 399 400 401 402 403 404 405 406 407 408 409 410 411 412 413 414 415 416 417 418 419 420 421 422 423 424 425 426 427 428 429 430 431 432 433 434 435 436 437 438 439 440 441 442 443 444 445 446 447 448 449 450 451 452 453 454 455 456 457 458 459 460 461 462 463 464 465 466 467 468 469 470 471 472 473 474 475 476 477 478 479 480 481 482 483 484 485 486 487 488 489 490 491 492 493 494 495 496 497 498 499 500 501 502 503 504 505 506 507 508 509 510 511 512 513 514 515 516 517 518 519 520 521 522 523 524 525 526 527 528 529 530 531 532 533 534 535 536 537 538 539 540 541 542 543 544 545 546 547 548 549 550 551 552 553 554 555 556 557 558 559 560 561 562 563 564 565 566 567 568 569 570 571 572 573 574 575 576 577 578 579 580 581 582 583 584 585 586 587 588 589 590 591 592 593 594 595 596 597 598 599 600 601 602 603 604 605 606 607 608 609 610 611 612 613 614 615 616 617 618 619 620 621 622 623 624 625 626 627 628 629 630 631 632 633 634 635 636 637 638 639 640 641 642 643 644 645 646 647 648 649 650 651 652 653 654 655 656 657 658 659 660 661 662 663 664 665 666 667 668 669 670 671 672 673 674 675 676 677 678 679 680 681 682 683 684 685 686 687 688 689 690 691 692 693 694 695 696 697 698 699 700 701 702 703 704 705 706 707 708 709 710 711 712 713 714 715 716 717 718 719 720 721 722 723 724 725 726 727 728 729 730 731 732 733 734 735 736 737 738 739 740 741 742 743 744 745 746 747 748 749 750 751 752 753 754 755 756 757 758 759 760 761 762 763 764 765 766 767 768 769 770 771 772 773 774 775 776 777 778 779 780 781 782 783 784 785 786 787 788 789 790 791 792 793 794 795 796 797 798 799 800 801 802 803 804 805 806 807 808 809 810 811 812 813 814 815 816 817 818 819 820 821 822 823 824 825 826 827 828 829 830 831 832 833 834 835 836 837 838 839 840 841 842 843 844 845 846 847 848 849 850 851 852 853 854 855 856 857 858 859 860 861 862 863 864 865 866 867 868 869 870 871 872 873 874 875 876 877 878 879 880 881 882 883 884 885 886 887 888 889 890 891 892 893 894 895 896 897 898 899 900 901 902 903 904 905 906 907 908 909 910 911 912 913 914 915 916 917 918 919 920 921 922 923 924 925 926 927 928 929 930 931 932 933 934 935 936 937 938 939 940 941 942 943 944 945 946 947 948 949 950 951 952 953 954 955 956 957 958 959 960 961 962 963 964 965 966 967 968 969 970 971 972 973 974 975 976 977 978 979 980 981 982 983 984 985 986 987 988 989 990 991 992 993 994 995 996 997 998 999 1000 1001 1002 1003 1004 1005 1006 1007 1008 1009 1010 1011 1012 1013 1014 1015 1016 1017 1018 1019 1020 1021 1022 1023 1024 1025 1026 1027 1028 1029 1030 1031 1032 1033 1034 1035 1036 1037 1038 1039 1040 1041 1042 1043 1044 1045 1046 1047 1048 1049 1050 1051 1052 1053 1054 1055 1056 1057 1058 1059 1060 1061 1062 1063 1064 1065 1066 1067 1068 1069 1070 1071 1072 1073 1074 1075 1076 1077 1078 1079 1080 1081 1082 1083 1084 1085 1086 1087 1088 1089 1090 1091 1092 1093 1094 1095 1096 1097 1098 1099 1100 1101 1102 1103 1104 1105 1106 1107 1108 1109 1110 1111 1112 1113 1114 1115 1116 1117 1118 1119 1120 1121 1122 1123 1124 1125 1126 1127 1128 1129 1130 1131 1132 1133 1134 1135 1136 1137 1138 1139 1140 1141 1142 1143 1144 1145 1146 1147 1148 1149 1150 1151 1152 1153 1154 1155 1156 1157 1158 1159 1160 1161 1162 1163 1164 1165 1166 1167 1168 1169 1170 1171 1172 1173 1174 1175 1176 1177 1178 1179 1180 1181 1182 1183 1184 1185 1186 1187 1188 1189 1190 1191 1192 1193 1194 1195 1196 1197 1198 1199 1200 1201 1202 1203 1204 1205 1206 1207 1208 1209 1210 1211 1212 1213 1214 1215 1216 1217 1218 1219 1220 1221 1222 1223 1224 1225 1226 1227 1228 1229 1230 1231 1232 1233 1234 1235 1236 1237 1238 1239 1240 1241 1242 1243 1244 1245 1246 1247 1248 1249 1250 1251 1252 1253 1254 1255 1256 1257 1258 1259 1260 1261 1262 1263 1264 1265 1266 1267 1268 1269 1270 1271 1272 1273 1274 1275 1276 1277 1278 1279 1280 1281 1282 1283 1284 1285 1286 1287 1288 1289 1290 1291 1292 1293 1294 1295 1296 1297 1298 1299 1300 1301 1302 1303 1304 1305 1306 1307 1308 1309 1310 1311 1312 1313 1314 1315 1316 1317 1318 1319 1320 1321 1322 1323 1324 1325 1326 1327 1328 1329 1330 1331 1332 1333 1334 1335 1336 1337 1338 1339 1340 1341 1342 1343 1344 1345 1346 1347 1348 1349 1350 1351 1352 1353 1354 1355 1356 1357 1358 1359 1360 1361 1362 1363 1364 1365 1366 1367 1368 1369 1370 1371 1372 1373 1374 1375 1376 1377 1378 1379 1380 1381 1382 1383 1384 1385 1386 1387 1388 1389 1390 1391 1392 1393 1394 1395 1396 1397 1398 1399 1400 1401 1402 1403 1404 1405 1406 1407 1408 1409 1410 1411 1412 1413 1414 1415 1416 1417 1418 1419 1420 1421 1422 1423 1424 1425 1426 1427 1428 1429 1430 1431 1432 1433 1434 1435 1436 1437 1438 1439 1440 1441 1442 1443 1444 1445 1446 1447 1448 1449 1450 1451 1452 1453 1454 1455 1456 1457 1458 1459 1460 1461 1462 1463 1464 1465 1466 1467 1468 1469 1470 1471 1472 1473 1474 1475 1476 1477 1478 1479 1480 1481 1482 1483 1484 1485 1486 1487 1488 1489 1490 1491 1492 1493 1494 1495 1496 1497 1498 1499 1500 1501 1502 1503 1504 1505 1506 1507 1508 1509 1510 1511 1512 1513 1514 1515 1516 1517 1518 1519 1520 1521 1522 1523 1524 1525 1526 1527 1528 1529 1530 1531 1532 1533 1534 1535 1536 1537 1538 1539 1540 1541 1542 1543 1544 1545 1546 1547 1548 1549 1550 1551 1552 1553 1554 1555 1556 1557 1558 1559 1560 1561 1562 1563 1564 1565 1566 1567 1568 1569 1570 1571 1572 1573 1574 1575 1576 1577 1578 1579 1580 1581 1582 1583 1584 1585 1586 1587 1588 1589 1590 1591 1592 1593 1594 1595 1596 1597 1598 1599 1600 1601 1602 1603 1604 1605 1606 1607 1608 1609 1610 1611 1612 1613 1614 1615 1616 1617 1618 1619 1620 1621 1622 1623 1624 1625 1626 1627 1628 1629 1630 1631 1632 1633 1634 1635 1636 1637 1638 1639 1640 1641 1642 1643 1644 1645 1646 1647 1648 1649 1650 1651 1652 1653 1654 1655 1656 1657 1658 1659 1660 1661 1662 1663 1664 1665 1666 1667 1668 1669 1670 1671 1672 1673 1674 1675 1676 1677 1678 1679 1680 1681 1682 1683 1684 1685 1686 1687 1688 1689 1690 1691 1692 1693 1694 1695 1696 1697 1698 1699 1700 1701 1702 1703 1704 1705 1706 1707 1708 1709 1710 1711 1712 1713 1714 1715 1716 1717 1718 1719 1720 1721 1722 1723 1724 1725 1726 1727 1728 1729 1730 1731 1732 1733 1734 1735 1736 1737 1738 1739 1740 1741 1742 1743 1744 1745 1746 1747 1748 1749 1750 1751 1752 1753 1754 1755 1756 1757 1758 1759 1760 1761 1762 1763 1764 1765 1766 1767 1768 1769 1770 1771 1772 1773 1774 1775 1776 1777 1778 1779 1780 1781 1782 1783 1784 1785 1786 1787 1788 1789 1790 1791 1792 1793 1794 1795 1796 1797 1798 1799 1800 1801 1802 1803 1804 1805 1806 1807 1808 1809 1810 1811 1812 1813 1814 1815 1816 1817 1818 1819 1820 1821 1822 1823 1824 1825 1826 1827 1828 1829 1830 1831 1832 1833 1834 1835 1836 1837 1838 1839 1840 1841 1842 1843 1844 1845 1846 1847 1848 1849 1850 1851 1852 1853 1854 1855 1856 1857 1858 1859 1860 1861 1862 1863 1864 1865 1866 1867 1868 1869 1870 1871 1872 1873 1874 1875 1876 1877 1878 1879 1880 1881 1882 1883 1884 1885 1886 1887 1888 1889 1890 1891 1892 1893 1894 1895 1896 1897 1898 1899 1900 1901 1902 1903 1904 1905 1906 1907 1908 1909 1910 1911 1912 1913 1914 1915 1916 1917 1918 1919 1920 1921 1922 1923 1924 1925 1926 1927 1928 1929 1930 1931 1932 1933 1934 1935 1936 1937 1938 1939 1940 1941 1942 1943 1944 1945 1946 1947 1948 1949 1950 1951 1952 1953 1954 1955 1956 1957 1958 1959 1960 1961 1962 1963 1964 1965 1966 1967 1968 1969 1970 1971 1972 1973 1974 1975 1976 1977 1978 1979 1980 1981 1982 1983 1984 1985 1986 1987 1988 1989 1990 1991 1992 1993 1994 1995 1996 1997 1998 1999 2000 2001 2002 2003 2004 2005 2006 2007 2008 2009 2010 2011 2012 2013 2014 2015 2016 2017 2018 2019 2020 2021 2022 2023 2024 2025 2026 2027 2028 2029 2030 2031 2032 2033 2034 2035 2036 2037 2038 2039 2040 2041 2042 2043 2044 2045 2046 2047 2048 2049 2050 2051 2052 2053 2054 2055 2056 2057 2058 2059 2060 2061 2062 2063 2064 2065 2066 2067 2068 2069 2070 2071 2072 2073 2074 2075 2076 2077 2078 2079 2080 2081 2082 2083 2084 2085 2086 2087 2088 2089 2090 2091 2092 2093 2094 2095 2096 2097 2098 2099 2100 2101 2102 2103 2104 2105 2106 2107 2108 2109 2110 2111 2112 2113 2114 2115 2116 2117 2118 2119 2120 2121 2122 2123 2124 2125 2126 2127 2128 2129 2130 2131 2132 2133 2134 2135 2136 2137 2138 2139 2140 2141 2142 2143 2144 2145 2146 2147 2148 2149 2150 2151 2152 2153 2154 2155 2156 2157 2158 2159 2160 2161 2162 2163 2164 2165 2166 2167 2168 2169 2170 2171 2172 2173 2174 2175 2176 2177 2178 2179 2180 2181 2182 2183 2184 2185 2186 2187 2188 2189 2190 2191 2192 2193 2194 2195 2196 2197 2198 2199 2200 2201 2202 2203 2204 2205 2206 2207 2208 2209 2210 2211 2212 2213 2214 2215 2216 2217 2218 2219 2220 2221 2222 2223 2224 2225 2226 2227 2228 2229 2230 2231 2232 2233 2234 2235 2236 2237 2238 2239 2240 2241 2242 2243 2244 2245 2246 2247 2248 2249 2250 2251 2252 2253 2254 2255 2256 2257 2258 2259 2260 2261 2262 2263 2264 2265 2266 2267 2268 2269 2270 2271 2272 2273 2274 2275 2276 2277 2278 2279 2280 2281 2282 2283 2284 2285 2286 2287 2288 2289 2290 2291 2292 2293 2294 2295 2296 2297 2298 2299 2300 2301 2302 2303 2304 2305 2306 2307 2308 2309 2310 2311 2312 2313 2314 2315 2316 2317 2318 2319 2320 2321 2322 2323 2324 2325 2326 2327 2328 2329 2330 2331 2332 2333 2334 2335 2336 2337 2338 2339 2340 2341 2342 2343 2344 2345 2346 2347 2348 2349 2350 2351 2352 2353 2354 2355 2356 2357 2358 2359 2360 2361 2362 2363 2364 2365 2366 2367 2368 2369 2370 2371 2372 2373 2374 2375 2376 2377 2378 2379 2380 2381 2382 2383 2384 2385 2386 2387 2388 2389 2390 2391 2392 2393 2394 2395 2396 2397 2398 2399 2400 2401 2402 2403 2404 2405 2406 2407 2408 2409 2410 2411 2412 2413 2414 2415 2416 2417 2418 2419 2420 2421 2422 2423 2424 2425 2426 2427 2428 2429 2430 2431 2432 2433 2434 2435 2436 2437 2438 2439 2440 2441 2442 2443 2444 2445 2446 2447 2448 2449 2450 2451 2452 2453 2454 2455 2456 2457 2458 2459 2460 2461 2462 2463 2464 2465 2466 2467 2468 2469 2470 2471 2472 2473 2474 2475 2476 2477 2478 2479 2480 2481 2482 2483 2484 2485 2486 2487 2488 2489 2490 2491 2492 2493 2494 2495 2496 2497 2498 2499 2500 2501 2502 2503 2504 2505 2506 2507 2508 2509 2510 2511 2512 2513 2514 2515 2516 2517 2518 2519 2520 2521 2522 2523 2524 2525 2526 2527 2528 2529 2530 2531 2532 2533 2534 2535 2536 2537 2538 2539 2540 2541 2542 2543 2544 2545 2546 2547 2548 2549 2550 2551 2552 2553 2554 2555 2556 2557 2558 2559 2560 2561 2562 2563 2564 2565 2566 2567 2568 2569 2570 2571 2572 2573 2574 2575 2576 2577 2578 2579 2580 2581 2582 2583 2584 2585 2586 2587 2588 2589 2590 2591 2592 2593 2594 2595 2596 2597 2598 2599 2600 2601 2602 2603 2604 2605 2606 2607 2608 2609 2610 2611 2612 2613 2614 2615 2616 2617 2618 2619 2620 2621 2622 2623 2624 2625 2626 2627 2628 2629 2630 2631 2632 2633 2634 2635 2636 2637 2638 2639 2640 2641 2642 2643 2644 2645 2646 2647 2648 2649 2650 2651 2652 2653 2654 2655 2656 2657 2658 2659 2660 2661 2662 2663 2664 2665 2666 2667 2668 2669 2670 2671 2672 2673 2674 2675 2676 2677 2678 2679 2680 2681 2682 2683 2684 2685 2686 2687 2688 2689 2690 2691 2692 2693 2694 2695 2696 2697 2698 2699 2700 2701 2702 2703 2704 2705 2706 2707 2708 2709 2710 2711

WHAT IS CLAIMED IS:

1. An absorbent material comprising:
 - (a) absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer;
 - (b) a polycationic polymer;
 - 5 (c) glue microfibers; and
 - (d) a carrier layer;wherein the polycationic polymer is bonded to the absorbent gelling particles; and the glue microfibers act as an adhesive between the absorbent gelling particles and the carrier layer.
2. The absorbent material of Claim 1, wherein the carrier layer is selected from the group consisting of a woven material and a nonwoven material.
3. The absorbent material of Claim 1, further comprising cellulose fibers dispersed in the absorbent gelling particles, wherein the cellulose fibers are adhered to the absorbent gelling particles by the glue microfibers.
4. The absorbent material of Claim 3, wherein the glue microfiber is selected from the group consisting of an elastomeric microfiber and a non-elastomeric microfiber.
5. The absorbent material of Claim 4, wherein the elastomeric microfiber is a thermoplastic polymeric meltblown microfiber.
6. The absorbent material of Claim 5, wherein the thermoplastic polymeric meltblown microfiber is an elastomeric Styrene-Isoprene-Styrene block copolymer.
7. The absorbent material of Claim 4, wherein the non-elastomeric microfiber is selected from the group consisting water-soluble microfiber and water-insoluble microfiber.
8. The absorbent material of Claim 7, wherein the water-soluble microfiber is selected from the group consisting of polyethyloxazoline, polyvinylpyrrolidone, ethylenevinylacetate copolymer glue and mixtures thereof.

9. The absorbent material of Claim 1, wherein the polycationic polymer is selected from the group consisting of polyamines, polyimines, and mixtures thereof.

10. The absorbent material of Claim 9, wherein the polyamine is selected from the group consisting of:

- (a) polymers having first amine groups;
- (b) polymers having second amine groups; and
- 5 (c) polymers having third amine groups.

11. The absorbent material of Claim 10, wherein the first amine is selected from the group consisting of a polyvinylamine, a polyallylamine and mixtures thereof.

12. The absorbent material of Claim 10, wherein the second amine is a polyethyleneamine.

13. The absorbent material of Claim 10, wherein the third amine is selected from the group consisting of a poly N, N-dimethylalkyl amine, a poly-N-alkylamine, and mixtures thereof.

14. The absorbent material of Claim 9, wherein the polyimine is selected from the group consisting of a polyethyleneimine, modified polyethyleneimines crosslinked with epihalohydrine, polyamidoamine grafted with ethyleneimine and mixtures thereof.

15. The absorbent material of Claim 1, wherein the absorbent gelling particles have an average particle size in the range of from about 10 μm to about 1000 μm .

16. The absorbent material of Claim 1, wherein the polycationic polymer chemically crosslinks to the water-insoluble absorbent hydrogel-forming polymer of absorbent gelling particles.

17. The absorbent material of Claim 1, wherein the absorbent material comprises from about 50% to about 90% of the absorbent gelling particle, from about 0.1% to about 10% of the polycationic polymer, from about 1% to

09171010 101200

about 10% of the thermoplastic polymeric microfiber and from about 5% to
5 about 50% of the carrier layer by weight.

18. The absorbent material of Claim 1, wherein the polycationic polymer have
a molecular weight of at least about 70,000.

19. An absorbent article comprising:

- (a) a liquid pervious topsheet;
- (b) a liquid impervious backsheet; and
- (c) an absorbent core positioned between the topsheet and the
5 backsheet, wherein the absorbent core comprises the absorbent material of
Claim 1.

20. An absorbent material comprising:

- (a) absorbent gelling particles comprising a water-insoluble absorbent
hydrogel-forming polymer;
 - (b) polycationic polymer comprising a polycationic polymer; and
 - 5 (c) a carrier layer;
- wherein the polycationic polymer fibers having a concentration of from
about 80% to 99% by weight are bonded to the absorbent gelling particles;
and the polycationic polymer fibers act as an adhesive between the
absorbent gelling particles and the carrier layer.

21. The absorbent material of Claim 20, wherein the polycationic polymer
fibers have a molecular weight of at least about 70,000.

22. An absorbent article comprising:

- (a) a liquid pervious topsheet;
- (b) a liquid impervious backsheet; and
- (c) an absorbent core positioned between the topsheet and the
5 backsheet, wherein the absorbent core comprises the absorbent
material of Claim 20.

23. A method of making an absorbent material comprising:

- (a) applying absorbent gelling particles comprising a water-insoluble
absorbent hydrogel-forming polymer onto a carrier layer;
- (b) applying glue microfibers onto the carrier layer; and

- 5 (c) applying a polycationic polymer onto the absorbent gelling particles to form a bond between the absorbent gelling particles and the polycationic polymer;

wherein the absorbent gelling particles adhere to the glue microfibers prior to the glue microfibers adhering to the carrier layer.

24. The method of making the absorbent material of Claim 23, further comprising the step of dispersing cellulose fibers into the absorbent gelling particles, wherein the glue microfibers act as an adhesive between the cellulose fibers and the absorbent gelling particles.

25. The method of making the absorbent material of Claim 23, wherein the absorbent gelling particles, the glue microfibers and the polycationic polymer are applied, respectively, by a first air stream, a second air stream and a third air stream.

26. The method of making the absorbent material of Claim 25, wherein the first and second air stream are integrated prior to the absorbent gelling particles and the glue microfibers adhering the carrier layer.

27. The method of making the absorbent material of Claims 26, wherein the second air stream containing the glue microfibers has a temperature of from about 100 °C to about 400 °C.

28. The method of making the absorbent material of Claim 23, wherein the polycationic polymer is applied onto the carrier layer as a solution of water and the polycationic polymer.

29. The method of making the absorbent material of Claim 28, wherein the solution containing the polycationic polymer has a concentration of from about 0.1% to about 10% by weight.

30. The method of making the absorbent material of Claim 23, wherein the polycationic polymer is applied onto the carrier layer in a solid state.

31. The method of making the absorbent material of Claim 23, further comprising the step of heating the resulting material of step (c) at a

temperature of from about 50 °C to about 300 °C so as to covalently bond the polycationic polymer to the water-insoluble absorbent hydrogel-forming polymer of the absorbent gelling particles.

32.A method of making an absorbent material, the method comprising the steps of:

- (a) forming a first air stream comprising absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer;
- (b) forming a second air stream comprising glue microfibers;
- (c) merging the second air stream with the first air stream to form an integrated air stream comprising a thorough mixture of the glue microfibers and the absorbent gelling particles;
- (d) directing the integrated air stream onto a carrier layer;
- (e) forming a third air stream comprising a polycationic polymer; and
- (f) directing the third air stream onto the carrier layer so the polycationic polymer bonds to the absorbent gelling particles.

33.A method of making an absorbent material, the method comprising the steps of:

- (a) forming a first air stream comprising absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer;
- (b) forming a second air stream comprising a polycationic polymer;
- (c) merging the second air stream with the first air stream to form an integrated air stream, wherein the polycationic polymer bonds to the absorbent gelling particles;
- (d) forming a third air stream comprising glue microfibers;
- (e) merging the integrated air stream with the third air stream to form a mixture air stream; and
- (f) directing the mixture air stream onto a carrier layer so the absorbent gelling particles bonded to the polycationic polymer adhere to glue microfibers, and the glue microfibers adhere to the carrier layer.

34.A method of making an absorbent material, comprising:

- (a) applying polycationic polymer fibers comprising a polycationic polymer having a concentration of from about 80% to about 99% by weight onto absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer; and
- (b) applying the absorbent gelling particles onto a carrier layer;

wherein the polycationic polymer fibers act as an adhesive between the absorbent gelling particles and the carrier layer.

35. The method for making the absorbent material of Claim 34, wherein the polycationic polymer fibers have the molecular weight of at least about 70,000.

36. The method of making the absorbent material of Claim 34, wherein the polycationic polymer fibers and the absorbent gelling particles are applied, respectively, by a first air stream and a second air stream.

37. The method of making the absorbent material of Claim 36, wherein the first and the second air stream are integrated prior to the glue microfibers adhering to the carrier layer.

38. A method of making an absorbent material, the method comprising the steps of:

- (a) forming a first air stream containing polycationic polymer fibers;
- (b) forming a second air stream containing absorbent gelling particles comprising a water-insoluble absorbent hydrogel-forming polymer;
- (c) merging the second air stream with the first air stream to form an integrated air stream, wherein the polycationic polymer fibers bond to the absorbent gelling particles; and
- (d) directing the integrated air stream onto a carrier layer so that the absorbent gelling particles bonded to the polycationic polymer fibers adhere to the carrier layer.

39. An absorbent article comprising the absorbent material of Claim 1.

40. The absorbent article of Claim 39, wherein the absorbent article is a diaper.


41. The absorbent article of Claim 39, wherein the absorbent article is a catamenial product.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 15/60, 15/58		(11) International Publication Number: WO 97/39780
A1		(43) International Publication Date: 30 October 1997 (30.10.97)
(21) International Application Number: PCT/US97/06603 (22) International Filing Date: 24 April 1997 (24.04.97) (30) Priority Data: 8/102736 24 April 1996 (24.04.96) JP (71) Applicant (for all designated States except US): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): REZAI, Ebrahim [US/JP]; 5-15-1302, Koyo-cho Naka, Higashinada-ku, Kobe 658 (JP). HSUEH, Kesyin [-/JP]; 4-17-15, Kitaogi #305, Higashinada-ku, Kobe 658 (JP). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: **ABSORBENT MATERIALS HAVING IMPROVED STRUCTURAL STABILITY IN DRY AND WET STATES AND MAKING METHODS THEREFOR**



(57) Abstract

An absorbent material having substantially improved structural stability in the dry and wet states. The absorbent materials are significantly less susceptible to handling losses of absorbent gelling particles during manufacturing operations. The absorbent material also is not subject to shifting of the absorbent gelling particles during or after swelling by fluids. The absorbent material comprises absorbent gelling particles comprising (a) a water-insoluble absorbent hydrogel-forming polymer; (b) a polycationic polymer bonded to the absorbent gelling particles at the surface thereof; (c) glue microfibers dispersed in the absorbent gelling particles; and (d) a carrier layer bonded to the absorbent gelling particles through the glue microfibers. The invention further relates to a method of making the absorbent materials, and the absorbent articles comprising the absorbent materials.

Sheet 6 of 6




FIG. 1

DECLARATION COMBINED WITH POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

"Absorbent Materials Having Improved Structural Stability In Dry And Wet States And Making Methods Therefor"

bearing the above listed Procter & Gamble Company Case number, the specification of which was filed as PCT/US97/06603, designating at least the United States of America, with the United States Receiving Office on 24 April 1997.

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37 Code of Federal Regulations §1.56.

I hereby claim foreign priority benefits under Title 35 United States Code §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application for patent or Inventor's certificate having a filing date before that of the application on which priority is claimed:

PRIOR FOREIGN APPLICATION(S) TO WHICH WE CLAIM PRIORITY:

H8-102736 JP 24 April 1996

I hereby claim the benefit under Title 35 United States Code §120 of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35 United States Code §112, I acknowledge the duty to disclose material information as defined in Title 37 Code of Federal Regulations §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Appln. Serial No.)	(Filing Date)	(Status)(patented, pending, abandoned)
---------------------	---------------	--

(Appln. Serial No.)	(Filing Date)	(Status)(patented, pending, abandoned)
---------------------	---------------	--

I hereby appoint the following as my attorney(s) or agent(s) with full power of substitution to prosecute this application and transact all business in the Patent and Trademark office connected therewith:

<u>Name</u>	<u>Registration No.</u>	<u>Associate Power of Attorney Attached</u> [] Yes [] No
Jacobus C. Rasser	<u>37,043</u>	
Donald E. Hasse	<u>29,387</u>	
T. David Reed	<u>32,931</u>	
Eileen L. Hughett	<u>34,352</u>	
George E. Dostie	<u>39,173</u>	

SEND CORRESPONDENCE TO:
T. David Reed, c/o The Procter & Gamble Company (513) 627-7025

<u>Name</u>	<u>Cincinnati</u>	<u>Ohio</u>	<u>Phone No.</u>
<u>5299 Spring Grove Avenue</u>			<u>45217-1087</u>
<u>Street</u>	<u>City</u>	<u>State</u>	<u>Zip Code</u>

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor: REZAI, Ebrahim (NMN)
Inventor's signature Ebrahim Rezaei Date 3/17/98

Residence: 5-15-1302, Koyo-cho Naka, Higashinada-Ku Kobe 658
JP JPX
Citizenship: US
Post Office Address: Procter & Gamble Far East, Inc.
17, Koyo-cho Naka 1-chome, Higashinada-ku, Kobe 658 Japan

Full name of second joint inventor, if any: HSUEH, Kesyin
Inventor's signature Kesying Hsueh Date 3/17/98

Residence: #305, 4-17-15, Kitaogi Higashinada-ku, Kobe 658
JP JPX
Citizenship: TW
Post Office Address: Procter & Gamble Far East, Inc., 17,
Koyo-cho Naka 1-chome, Higashinada-ku, Kobe 658 Japan

Full name of third joint inventor, if any:
Inventor's signature _____ Date _____

Residence: _____
Citizenship: _____
Post Office Address: _____

Full name of fourth joint inventor, if any:
Inventor's signature _____ Date _____

Residence: _____
Citizenship: _____
Post Office Address: _____

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In the matter of

U. S. National Phase Entry
Under 35 USC 371 from
the International Application of
REZAI, Ebrahim et al
Int'l Application No. PCT/US97/06603
Filed in the RO/US on 24 April 1997
Entitled: Absorbent Materials Having
Improved Structural Stability in
Dry and Wet States and Making
Methods Therefor

:
: "Express Mail" mailing label number: EM03270735645
: Date of Deposit: 12 Oct. 1998
: I hereby certify that the above matter has been being
: deposited with the United States Patent Service Express
: Mail Post Office to and from the United States Patent and
: on the date indicated above and is referred to the
: Commissioner for Patents and Trademarks, Washington,
: D.C. 20231.
: Donna L. Butts
: Name
: Donna L. Butts
: Signature

ASSOCIATE POWER OF ATTORNEY

Assistant Commissioner for Patents
Box PCT
Washington, D.C. 20231

Dear Sir:

You are requested to recognize M. C. Hentz (Registration No. 37,556); D. M. Weirich (Registration No. 38,361); E. J. Milbrada (Registration No. 40,090); S. W. Miller (Registration No. 31,984); and J. C. Rasser (Registration No. 37,043) of The Procter & Gamble Company, Cincinnati, Ohio, as Associate Attorney to prosecute this application, to make alterations and amendments therein, and to transact all business in the Patent Office connected with the application or with the patent granted thereupon.

Please address all future communications to:

M. C. Hentz, Patent Attorney
Patent Division
The Procter & Gamble Company
Winton Hill Technical Center
6083 Center Hill Avenue
Cincinnati, OH 45224

Respectfully submitted for Applicants,

By Eileen L. Hughett
Eileen L. Hughett
Agent for Applicant
Registration No. 34,352

5299 Spring Grove Avenue
Cincinnati, Ohio 45217
09 September 1998
(513) 627-7025/FAX 627-6333